





特钢精密异形材

SPECIAL SHAPED STEEL



最大程度为您**节约**宝贵材料，**减少**后道加工，**提升**产效。

Maximum extent to save valuable material, reduce after processing, improve production efficiency

运用领域
Application

刀具、模具、导轨、汽车配件、电器配件、机床配件等
Blades, mold, guide rail, electrical accessory, Machine tool accessories, etc

交货状态
Condition of delivery

盘卷、直条、定制尺寸
coil, bar, customized dimension

材质成份 Material

对应国际钢号				化学成分及含量%												
Corresponding to international standard				Chemical composition and content%												
GB	AISI	DIN	JIS	C	Mn	P ≤	S ≤	Si	Cr	V	W	Mo	Co			
W6Mo5Cr4V2	M2	HS6-5-2	SKH51	0.8-0.9	0.15-0.40	0.03	0.03	0.20-0.45	3.80-4.40	1.75-2.20	5.50-6.75	4.50-5.50				
CW6Mo5Cr4V3	M3 Class	HS6-5-3	SKH53	1.15-1.25	0.15-0.40	0.03	0.03	0.20-0.45	3.75-4.50	2.75-3.25	5.00-6.75	4.75-6.50				
M4	M4	TSP4		1.25-1.40	0.15-0.40	0.03	0.03	0.20-0.45	3.75-4.50	3.75-4.50	5.25-6.50	4.50-5.50				
W2Mo9Cr4VCo8	M42	HS2-9-1-8	SKH59	1.05-1.15	0.15-0.40	0.03	0.03	0.15-0.65	3.50-4.25	0.95-1.35	1.15-1.85	9.0-10.0	7.75-8.75			
W6Mo5Cr4V2Co5	M35	HS6-5-2-5	SKH55	0.87-0.95	0.15-0.40	0.03	0.03	0.20-0.45	3.75-4.50	1.70-2.10	5.50-6.70	4.70-5.20	4.50-5.00			
W18Cr4V	T1	HS18-0-1	SKH2	0.70-0.80	0.15-0.40	0.03	0.03	≤0.40	3.80-4.40	1.00-1.40	17.5-19.0	≤0.30				
Cr12MoV	D2		SKD11	1.45-1.70	≤0.40	0.03	0.03	≤0.40	11.00-12.50	0.15-0.30		0.40-0.60	≤1.00			
95Cr18	440C		SUS440C	0.90-1.00	≤0.80	0.035	0.03	≤0.80	17.00-19.00							
95Cr18Mo	440C		SUS440C	0.90-1.00	≤0.80	0.035	0.03	≤0.80	16.00-18.00			≤0.75				
Gcr15		100Cr6	SUJ2	0.95-1.05	0.25-0.45	0.025	0.025	0.15-0.35	1.40-1.65			≤0.10				